

6820 ACRYLIC PRIMER GRAY

PRODUCT DESCRIPTION:

6820 Acrylic Primer Surfacer is a one-component high build primer made of the highest quality acrylic available. This primer dries fast and sands easily within 30 minutes of application. This primer provides excellent filling and adhesion as well as superior color holdout. 6820 can be topcoated with lacquers, enamels, and polyurethanes after sealing. Designed to be used only with high quality virgin lacquer thinner at 1:1 mix ratio. Mixed properly with good lacquer thinner, 6820 resists settling.

FEATURES:

1. Very fast dry, sand within 30 minutes
2. Superior adhesion to: Cured finishes, Body fillers, Sanded fiberglass, Bare steel
3. Superior filling and sanding properties
4. Superior color holdout
5. Easy 1:1 mix ratio (use only virgin lacquer thinner with V.O.C. of 1.3 lbs. per gallon for V.O.C. compliance, such as SF-10, SF-20, SF-25)
6. Low cost
7. 6820 Gray is tintable with 10% color

SURFACE PREPARATION:

1. Wash area to be primed with detergent (any non-silicon soap) and hot or cold water.
2. Clean area with CP-90 Pre-Clean.
3. Apply primer as needed, after sanding primer clean with CP-90 Pre-Clean.

MIXING INSTRUCTIONS:

1. Shake or stir 6820 thoroughly before reducing (if shaking, allow to set 20-30 minutes before reducing and spraying).
2. Reduce equal parts of 6820 primer with virgin lacquer thinner (1.3 lbs V.O.C., to be compliant).
...Note: Thinners containing reclaimed solvents can adversely affect primer performance.

APPLICATION INSTRUCTIONS:

1. Use 35 P.S.I. air pressure at gun.
2. Apply 2 to 3 medium wet coats allowing ample flash time between coats.
3. Allow primer to dry 30 minutes before sanding depending on weather conditions.
4. Finish sand with 320 grit or finer sand paper.

CLEANING:

Use good quality lacquer thinner (CP-5/10/15/20/25) or urethane reducer (CP-80/CP-81/CP-82/CP-83) to thoroughly clean all equipment.

TECHNICAL DATA:

Coverage 1 mil:	381 sq. ft
Mix Ratio:	1:1
Sprayable Viscosity:	24 sec. #2 Zahn
Flash Point:	-20 F
Film Build (DFT):	1.5 mils per double coat
Dry to Sand:	30 minutes
Color Holdout:	Excellent
Fill Properties:	Excellent
Solids by Weight:	40%
Solids by Volume:	23.8%
V.O.C. (Sprayable) using Lacquer Thinner of 1.3 lbs. Per gallon and 1:1 mix ratio:	4.81 lbs. Per gallon
Unreduced V.O.C.:	4.3 lbs. Per gallon